

# Raffino - Technical information

*Tile collection performance based on industry standards.*

## Technical Information

|   |                     |                                    |                        |
|---|---------------------|------------------------------------|------------------------|
|  | WATER ABSORPTION    | ANSI / ISO - (%)                   | 10% ≤E ≤18% - P4       |
|  | ABRASION RESISTANCE | ANSI / ISO                         | CLASS 0                |
|  | SCRATCH HARDNESS    | ANSI / ISO - (Mohs)                | 4                      |
|  | BREAKING STRENGTH   | ANSI - (lbf)<br>ISO - (N)          | >230<br>>950           |
|  | SHADE VARIATION     |                                    | V2                     |
|  | SLIP RESISTANCE     | ANSI - DCOF (WET)<br>ISO - R VALUE | MATTE N/A<br>MATTE N/A |
|  | CHEMICAL RESISTANCE | ANSI / ISO                         | CLASS B                |
|  | STAIN RESISTANCE    | ANSI<br>ISO                        | CLASS B<br>CLASS 4     |
|  | FROST RESISTANCE    | ANSI / ISO                         | NOT RESISTANT          |

Test values are based on ANSI / ISO standards according to: ANSI A137.1 Non-Vitreous P4 Class, ISO 13006 - L - Group BIII, EN 14411 - L - Group BIII. Variances in test values can occur in different production lots.

## Usage recommendation

*Anatolia's recommendations for suitable applications.*

### Usage Recommendations\*

MATTE GLAZED CERAMIC

| APPLICATION |                          | WALL | FLOOR |
|-------------|--------------------------|------|-------|
| INTERIOR    | RESIDENTIAL              | •    |       |
|             | COMMERCIAL               | •    |       |
|             | HEAVY COMMERCIAL         |      |       |
| EXTERIOR    | RESIDENTIAL / COMMERCIAL |      |       |

\* These recommendations are not defined by ANSI/ISO standards.